



Sil-Free™: 101700F00000G

101700F00000G is a 43 gram (1.5 oz.) syringe of Sil-Free. Representative Image Only

- Buy Product
- Get a Sample
- Request a Quote

Select Product Variation

101700F00000G ▼

Price per piece

Quantity

[Add to Cart](#)

[Product Details](#)
[Data & Performance](#)
[Downloads](#)

Product Overview

Sil-Free™

Color: White
 Thermal Conductivity: 0.79 W/(m-°C)
 Operating Temperature Range: -40°C to 200°C
 Volume Resistivity: 2.3 x 10¹² Ohm-cm
 Weight: 47.5 grams
 Dielectric Strength: 8860 Volts/mm
 Consistency: Paste
 Bleed: 0.09 max
 Specific Gravity: 2.8
 Shelf Life: 5 years unopened*

*It is recommended that the containers be turned over every 6 months to minimize settling for ease of mixing.

101700F00000G

Color: White
 Thermal Conductivity: 0.79 W/(m-°C)
 Operating Temperature Range: -40°C to 200°C
 Volume Resistivity: 2.3 x 10¹² Ohm-cm
 Weight: 47.5 grams
 Dielectric Strength: 8860 Volts/mm
 Consistency: Paste
 Bleed: 0.09 max
 Specific Gravity: 2.8
 Shelf Life: 5 years unopened*

*It is recommended that the containers be turned over every 6 months to minimize settling for ease of mixing.

Support

[Locations](#)
[Privacy Policy](#)

About Aavid

[Products](#)
[Manufacturing Capabilities](#)

Follow Us

[Newsletter Sign Up](#)

[Terms and Conditions](#)
[Return Policy](#)
[Regulatory
and Compliance](#)

[Design & Engineering
Services](#)
[Boyd Corporate Website](#)

