

ON Semiconductor			10/15/2019	
Base Part		MOC3041M		Pb-free
Orderable Part		MOC3041VM	Total weight (mg)	449.722
Homogenous Material	Weight (mg)	Substance in Mat.	CAS #	% Avg. Weight
Coupling Gel	0.4	Dimethyl Cyclosiloxanes	69430-24-6	10
		Trimethoxy(methyl)silane (C4H12O3Si)	1185-55-3	90
Die	5.13	Silicon (Si)	7440-21-3	100
Die Attach	0.3	Silver (Ag)	7440-22-4	75
		Phenolic Resin-2	54208-63-8	25
Lead Frame	108.322	Silver (Ag)	7440-22-4	0.62775798
		Zinc (Zn)	7440-66-6	0.12001256
		Iron (Fe)	7439-89-6	2.28947028
		Copper (Cu)	7440-50-8	96.93321763
		Phosphorus (P)	7723-14-0	0.02954155
Mold Compound-White	327.22	Titanium Dioxide (TiO2)	13463-67-7	25
		Brominated Bisphenol A Diglycidyl Ether	40039-93-8	3
		Ortho Cresol Novolac Resin	29690-82-2	13.5
		Antimony Trioxide (Sb2O3)	1309-64-4	3
		Fused Silica (SiO2)	60676-86-0	50
		Phenolic Resin (Novolac)	9003-35-4	5.5
Plating	6.7	Tin (Sn)	7440-31-5	100
Wire Bond - Au	1.65	Gold (Au)	7440-57-5	100
<p>Materials Disclosure Disclaimer: Even though all possible efforts have been made to provide you with the most accurate information, we cannot guarantee to its accuracy since the data has been compiled based on the ranges provided, and some information provided by the subcontractors and raw material suppliers may have been withheld to protect their business proprietary information. Thus this information is provided only as estimates, and do not include trace levels fo dopants and metal materials contained within silicon devices in the finished products. There is no intentional use of Mercury, Hexavalent Chromium, Cadmium, PBB or PBDE (5 of the 6 RoHS banned substances) in this or any of our other products. For further explanation on material composition calculations, please view our Product Chemical Content Brochure at:</p> <p>http://www.onsemi.com/pub/Collateral/BRD8022-D.PDF</p>				